

r-HIPS-HX | TDS

※The data in the table above is for reference only
Laboratory environment: temperature 23°C, relative humidity 50%



Contact us:
Tel.+86 15066260005
E-mail: info@gonplastics.com
<http://www.gonplastics.com>
Add: West Coast New District, Qingdao City, Shandong Province

Property/Test Condition	Unit	Values
Melting Flow Rate	g/10min	4.6
Ash Content	%	2.1
Izod Notched Impact	KJ/m2	5.62
Tensile Strength	MPa	36
Elongation at Break	%	39.2
Flexural Strength	MPa	64
Flexural Modulus	MPa	2648.5