

GON550N**技术参数表**

通用级聚苯乙烯 (GPPS)

Technical Data Sheet

产品描述 Product Description

GON550N 是一种高度透明的 GPPS，具有机械性能和耐热性能优异、易加工、成型周期短等特点。

GON550N is a highly transparent GPPS grade. It gives excellent mechanical and heat resistance properties while providing with easy process-ability and short cycle time.

特点 FEATURES

- 优异透明性
Excellent clarity
- 良好的机械和耐热性能
Good mechanical and heat resistance properties
- 易于加工，成型周期短
Easy process-ability with short cycle time
- 食品接触安全
Food contact compliant

应用 APPLICATIONS

- 双向拉伸聚苯乙烯片材
BOPS
- 装饰板，包括广告板、橱柜板、镜面墙板
Decorative board, including advertising board, cabinet board, mirror wall panels

产品性能**标准****测试条件****单位****典型值****Property****Standard****Test Condition****Unit****Typical Value****流变性能 Rheological Properties**

熔体质量流动速率 Melt Mass Rate	GB/T 3682.1 ISO 1133	200 °C/5 kg	g/10 min	2.0
----------------------------	-------------------------	-------------	----------	-----

机械性能 Mechanical Properties

简支梁无缺口冲击强度 Charpy Impact Strength	GB/T 1043.1 ISO 179/1eA	2J, Unnotched	KJ/m ²	15
拉伸强度 Tensile Strength	GB/T 1040.2 ISO 527	50mm/min	MPa	55
拉伸断裂伸长率 Tensile Elongation	GB/T 1040.2 ISO 527	50mm/min	%	4
弯曲强度 Flexural Strength	GB/T 9341 ISO 178	2mm/min	MPa	100
弯曲模量 Flexural Modulus	GB/T 9341 ISO 178	2mm/min	MPa	3000

热学性能 Thermal Properties

维卡软化温度 Vicat Softening Temperature	GB/T1633 ISO 306	B50 法, 50N, 50°C/h	°C	100
热变形温度 Heat Deflection Temperature	GB/T1634.1 ISO 75	0.45MPa, 120°C/h 未退火 Unannealed	°C	91

产品性能 Property	标准 Standard	测试条件 Test Condition	单位 Unit	典型值 Typical Value
电性能 Electrical Properties				
绝缘强度 Dielectric Strength	GB/T1408.1 IEC 60243-1	短时 Short Time, 1.5 mm	g/10 min	135
相对介电常数 (100 Hz) Relative Permittivity (100 Hz)	GB/T 31838.6 IEC 62631-2-1	100Hz	kV/mm	2.5
相对介电常数 (1 MHz) Relative Permittivity (1 MHz)	GB/T 31838.6 IEC 62631-2-1	1MHz	/	2.5
体积电阻率 Volume Resistivity	GB/T 31838.2 IEC 62631-3-1	23°C	Ohm*m	>10 ¹⁶
表面电阻率 Surface Resistivity	GB/T 31838.3 IEC 62631-3-2	23°C	Ohm	>10 ¹⁴
光学性能 Optical Properties				
透光率 Light Transmittance	GB/T 2410-2008 ASTM D 1003	23°C	%	91
雾度 Haze	GB/T 2410-2008 ASTM D 1003	23°C	%	0.3
其它性能 Other Properties				
密度 Density	GB/T1033 ISO 1183	23°C	Kg/m ³	1030
吸水率 Water absorption	GB/T 1034 ISO 62	23°C, 24h	%	0.1
燃烧性 Flammability	UL-94	Thickness 1.5mm All Color	/	HB
成型收缩率 Linear Mold Shrinkage	GB/T17037 ISO 294-4	23°C	%	0.4-0.7

加工参数 Processing Parameters	单位 Unit	典型值 Typical Value
预处理 (如果必要) Pre-treatment (If necessary)		
烘干温度 Drying Temperature	°C	70-80
烘干时间 Drying Time	Hour	2-4
最大含水率 Maximum Moisture Content	%	0.1
通用指南 General Guidelines		
熔体温度范围 Melt Temperature Range	°C	180-260
料筒温度 Barrel Temperature	前部 Front	°C 220-240
	中部 Middle	°C 210-235
	后部 Rear	°C 190-210
机头温度 Extruder Head Temperature	°C	220-245
辊温范围 Roller Temperature Range	°C	70-110

注意 Note:

- 1、上述所有数据仅为未着色产品的典型值，不同颜色之间可能略有差异。
Please note that all data stated are only Typical values for uncolored products, not specifications, and may vary slightly with different colors.
- 2、加工指南仅供参考，具体设置请遵循产品和机器条件，详情请咨询我们当地的销售或技术代表。
The general guidelines are only for reference. Exact settings have to follow the product and machine conditions. Please consult our local sales or technical representatives for details.
- 3、GON550N 以圆柱形颗粒形式供应。它应保存在原始包装中，或存放在干燥、凉爽的地方，避免直接暴露在阳光下。
GON550N is supplied as cylindrical shaped granules. It has to be kept in its original containers in a dry, cool place. Avoid direct exposure to sunlight.

免责声明 Disclaimer:

本技术数据表中的任何数据都不构成关于产品特性、产品对特定用途或应用的适用性或其可加工性的保证或陈述。国恩一塑不承担与此有关的一切责任。顾客必须亲自验证产品是否适合进一步的加工或应用，以及产品是否符合相关的法规要求。除非另有明确的单独的书面协议，否则国恩一塑对其产品的唯一和排他性责任在国恩一塑的一般销售条款和条件中规定。

Please note that no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its process-ability. GON Polymer.1 disclaims all liability in connection therewith. The customer himself is required to verify whether the product is suitable for the further processing or application intended and whether the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, GON Polymer.1's sole and exclusive liability with respect to its products is set forth in GON Polymer.1's General Terms and Conditions for Sale.